

Arova Style

1336

Water-based hardwood stain for a uniform, leveling stain finish **for industrial and professional use**

PRODUCT DESCRIPTION

General

Water-based hardwood stain with good light fastness for particularly even stain effects on fine and coarse-pored hardwoods. The product can be coated with water-based and solvent-based wood varnishes.

Special properties and standards



- **French ordinance DEVL1104875A**
Marking of construction coating products for their emission of volatile pollutants: A+

Application area



For furniture, interior fixtures, wall paneling and wood ceilings.

Depending on the furniture coating used, the product is suitable for surfaces of furnitures and interior finishing in application areas II – IV according to ÖNORM A 1610-12.

Application in combination with a suitable topcoat system.

PROCESSING

Processing instructions



- Please stir product well before and during use.
- The temperature of the product and object, and the room temperature must be at least + 15 °C.
- A staining application with Airmix or Airless low pressure device is also possible. An application with brush or sponge is also possible on small dimensioned surfaces.
- Less absorbent wood types require less application compared to more absorbent timber.
- The use of dark colors on light woods is not recommended.
- Various types of wood such as Oak, various exotic woods, etc. contain water-soluble substances, which become active when overcoating with water-based furniture coatings. To prevent discolouration or marks when painting wood rich in active substances we therefore recommend priming them first with Aduro Primer (2523).
- The color changes if the liquid stain comes into contact with metal.
- Do not return the product from the application tool or product contaminated with wood dust to the original container.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.
- Please observe our **ARL 110 - Working guidelines for staining Wood**.

Application technique

	Cup gun
Spraying nozzle Ø (mm)	1,5
Spraying pressure (bar)	1,5 - 2,5
Yield per application (m ² /l)	8
Applied quantity per application (g/m ²)	50 - 60

The stated yield includes spray loss.

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

(at 23 °C and 50 % rel. humidity)



Recoatable (solvent-based coatings)	12 hour(s)
Recoatable (water-based coatings)	5 hour(s)

Forced drying with circulating air must not be used in the first phase of drying.

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Avoid direct sunlight!

Cleaning the working equipment

8029

With water immediately after use.

To remove dried paint residues we recommend using Aqua-Cleaner (8029) (diluted 1:1 with water).

SUBSTRATE**Type of substrate**

Fine pored and coarsely porous hardwoods

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

Substrate preparation

Wood sanding Grit size 150 – 180

Rinsing the sanded wood and, once it has dried, sanding it smooth with grit size 150-180 is beneficial.

COATING SYSTEM**Stain application**

Apply uniformly along the direction of the wood fiber using the wet on wet method with slight excess so that the surfaces appear slightly moist.

Subsequent coating

2 x painting with ADLER furniture varnish, with intermediate sanding

The product can be coated with both water- and solvent-based ADLER furniture coatings. For light stain shades and color tones, we generally recommend the use of lightfast varnishes such as Bluefin Resist, Aduro Legnopur. When using non-lightfast types of paint, it can be expected that the final color will appear slightly yellowish; this effect increases with aging.

For white stained surfaces we recommend to apply additionally one layer of Legnopur, tinted with 1.0 % up to a max. of 3.0 % Solva-Tint Polarweiß (9035040114). Alternatively, a water-based furniture varnish such as Bluefin Top-Antiscratch, tinted with 1.0 to max. 3.0 % Aqua-Tint Polarweiß (9009040114), can be used. Avoid overlapping when spraying!

ORDERING INFORMATION

Size of trading unit 0.9 l, 4 l

Colour shades / Glosslevels



1336400100

Standard colour(s):

Farblos (1336400100)
 London (1336042001)
 Athen (1336042002)
 Mailand (1336042003)
 Madrid (1336042004)
 Wien (1336042005)
 Oslo (1336042006)
 Berlin (1336042007)
 Tokio (1336042008)
 Rom (1336042009)
 Barcelona (1336042010)
 Prag (1336042011)
 Nizza (1336042012)
 Riga (1336042013)
 Triest (1336042014)
 Bern (1336042015)

All colours can be mixed with each other and, if required, diluted with Arova Style Farblos (1336400100).

If it is thinned excessively, the inherent color of the wood and the natural yellowing of the wood can lead to noticeable color changes over a period of time.

Prior to applying the stain and the coating, you should always stain a sample on the original wood and treat it with the intended coating material in order to assess the final colour shade. Only use stains from the same batch for a commission.

Supplementary products

Aduro Legnopur (2513)
 Aduro Primer (2523)
 Aqua-Cleaner 8029 (8029)
 Aqua-Tint Polarweiß (9009040114)
 Bluefin Resist (2963)
 Bluefin Top-Antiscratch (2960)
 Solva-Tint Polarweiß (9035040114)

Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS

Durability / storage



Min. 1 year(s) in the original sealed containers.

Cool, but frost-free.

Safety information



The product is only suitable for the industrial and professional use.

The inhalation of paint aerosols during spray application must generally be avoided. This is ensured by the proper use of a respirator (combination filter A2/P2).

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.